

## BIANCO RETRO KRAFT WTL

TECHNICAL DATA SHEET: CARTONCINO BIANCO/KRAFT WTL

PARAMETERS		METHOD	UNIT	VALUES				
GRAMMAGE		ISO 536	g/m <sup>2</sup>	120	145	160	175	185
CALIPER		ISO 534	µm	145	180	195	210	220
SCOTT BOND		TAPPI T569	J/m <sup>2</sup>	350	350	350	350	350
BURST STRENGTH		ISO 2759	kPa	580	710	780	850	900
SCT	CD	ISO 9895	kN/m	2,8	3,2	3,6	4,0	4,4
TENSILE STIFFNESS	MD	ISO 1924	kN/m	950	1150	1250	1350	1450
	CD		kN/m	500	600	700	800	900
ROUGHNESS PPS-10	PS	ISO 8791-4	µm	1,3	1,4	1,5	1,6	1,7
GLOSS	PS	TAPPI T480	%	45	45	45	45	45
BRIGHTNESS	PS	ISO 2470	%	80	80	80	80	80
WHITENESS D65	PS	ISO 11475	%	80	81	81	81	81
COBB	PS	ISO 535	g/m <sup>2</sup>	34	34	34	34	34
	RS		g/m <sup>2</sup>	38	38	38	38	38
MOISTURE		ISO 287	%	7,0	7,0	7,0	7,0	7,0