

# OFFSET PREMIUM

## Cut size Paper

Items	Unit	Standards	A					
			65	68	70	75	78	80
Grammage	g/m <sup>2</sup>	GB/T451.2 ISO536	65±2	68±2	70±2.5	75±2.5	78±3	80±3
Thickness	µm	GB/T451.3 ISO534	92±4	94±4	97±4	100±4	106±4	106±4
Cobb-Top/Back (60s)	g/m <sup>2</sup>	GB/T1540 ISO535	≤45					
-Top/Back Brightness (D65)	%	GB/T7974 ISO2470	100.0±5.0					
CIE CIE Brightness	%	GB/T22880 ISO11475	155.0±5.0					
Opacity	%	GB/T1543 ISO1924	≥88.0					
BEKK Smoothness	S	GB/T456 ISO5627	≥15					
Moisture	%	GB/T462 ISO287	4.5±1.0					
Dirt	Spots/m <sup>2</sup>	GB/T1541	0.3-1.5mm <sup>2</sup> ≤60					
			(>0.5-1.5)mm <sup>2</sup> ≤6;					
			>1.5mm <sup>2</sup> ,no					
Tensile index MD	N.m/g	GB/T12914 ISO1924	≥40.0					

### Testing Condition:

Temperature: (23±1) °C

Relative Humidity: (50±2) %RH



Il marchio della  
gestione forestale  
responsabile