

MM Kwidzyn Sp. z o.o.
 ul. Lotnicza 1
 82-500 Kwidzyn
 Poland



TECHNICAL DATA SHEET

SPEED-E OFFSET

Parameter	Standard	Unit	Measurement					
Substance	EN ISO 536	g/m ²	60 ± 2	70 ± 2	75 ± 2 *	80 ± 2	90 ± 2	100 ± 2
Thickness	ISO 534	µm	77 ± 3	89 ± 3	96 ± 3	101 ± 3	112 ± 4	124 ± 4
Moisture content	EN ISO 287	%	6 ± 1	6 ± 1	6 ± 1	6 ± 1	6 ± 1	6 ± 1
Whiteness	ISO 11475	CIE units	146 ± 3	146 ± 3	146 ± 3	146 ± 3	146 ± 3	146 ± 3
Opacity	ISO 2471	%	84 +2/-1	89 +2/-1	90 +2/-1	92 +2/-1	93 +2/-1	94 +2/-1
Bendtsen Roughness	ISO 8791-2	ml/min	160 ± 50	160 ± 50	160 ± 50	160 ± 50	160 ± 50	160 ± 50
Cobb ₆₀	EN ISO 535	g/m ²	≤30	≤30	≤30	≤30	≤30	≤30
Tensile Strength	EN ISO 1924-2	kN/m	3,8 ± 1	4,0 ± 1	4,0 ± 1	4,0 ± 1	4,0 ± 1	4,5 ± 1

* Subject to trim and accumulation. For more information contact your dedicated customer service team.

Certification

✓ 100% ECF Fibres

The data presented can be changed without notice.