

CORABB NATURAL

Indicative Specifications



Thickness	Grammage	Bending Resistance L&W (15°)		Bending Moment Taber (15°)		Moisture (130°)
		MD, mN	CD, mN	MD, mNm	CD, mNm	
μm	g/m ²					%
350	240	280	104	13.5	5.0	8.5
400	263	400	163	19.3	7.9	8.5
450	284	520	190	25.1	9.2	8.5
500	312	720	267	34.8	12.9	8.5
550	337	840	312	40.6	15.1	8.5
630	387	1080	400	52.2	19.3	8.5
700	421	1330	493	64.3	23.8	8.5

Other properties

Scott Plybond	175 J/m ²
COBB (60s) Back Liner	35 g/m ²
COBB (180s) Back Liner	50 g/m ²