



ITC LIMITED – PSPD, UNIT: BOLLARAM

SPECIFICATION SHEET

Doc. No: SP/TES/FP/40	Ver. No: 7.0	Rev. No: 1.0	Page 1of 1	Issue Date: 01.07.2023
Grade Name	FILOBEV 2S			
Grade Id	FDRF			
SPEC NO	2FDRF /MGTH/PSPD/BOL/BAR			

SUBSTANCE (GSM)	CALIPER (µM)	BENDING RESISTANCE(L&W) mN		
		Tappi T 556		
Tappi T 410	Tappi T 411	MD	CD	GM
180	230	61	28	41
190	243	82	38	56
200	257	93	43	63
210	270	103	48	70
220	284	117	54	79
230	297	134	62	91
240	311	151	70	103
250	324	158	73	107
260	338	188	87	128
270	351	225	96	147
280	365	238	110	162
290	378	281	130	191
300	392	311	143	211
310	405	330	153	225
320	419	352	163	240
330	432	359	166	244
340	446	380	176	259
350	459	402	186	273
TOL : ± 5%	± 5%			±15%

PARAMETER	UNITS	VALUE
COBB (3 Mins) TOP BACK	GSM	ZERO ZERO
QS/TM/09 , Tappi T441		
MOISTURE Tappi T 412	%	6 ± 1
ROUGHNESS - BENDSTEN (Avg.) TOP BACK	ml/min	250 (350 MAX) 250 (350 MAX)
ISO 8791-2		
EDGEWICK - LA/23 TP84010	Kg/m ² /Hour	1.4 MAX
STRETCH MD CD	%	2.2 MIN 5.5 MIN
Tappi T 494		

Construction



Note :
 1.) All Properties are according to ITC Limited, PSPD Unit:BOL Measurements
 2.) Test Climate 23°C ± 1 & 50% ± 2 RH
 3.) Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples
 4.) This product can be serviced with FSC Mix. Certificate Registration Code: SW CoC 004747 - B

ACCEPTED BY	HEAD MARKETING (PSPD)	ISSUED BY	UNIT HEAD (BOL)
SIGNATURE		SIGNATURE	