



**ITC LIMITED – PSPD, UNIT: BOLLARAM**

**DEV SPECIFICATION SHEET**

Doc. No: SP/TES/FP/40      Ver. No: 7.0      Rev. No: 0.0      Page 1of 1      Issue Date: 01.03.2024

Grade Name: **FILOBEV PREMIUM 1S**  
 Grade Id: **FBPR**  
 SPEC NO: **1FBPR/CTX/PSPD/BOL/BEV**

SUBSTANCE (GSM)	CALIPER (µM)	BENDING RESISTANCE(L&W) mN		
		Tappi T 556		
Tappi T 410	Tappi T 411	MD	CD	GM
186	225	72	31	47
216	263	99	43	65
246	300	128	56	85
266	325	161	70	106
296	363	274	119	181
311	375	292	127	193
326	400	319	173	235
356	438	409	208	292
TOL : ± 5%	± 5%			±15%

PARAMETER	UNITS	VALUE
COBB ( 3 Mins) TOP BACK	GSM	35 MAX ZERO
QS/TM/09 , Tappi T441		
MOISTURE Tappi T 412	%	6 ± 1
ROUGHNESS - PPS (Avg.) TOP	ml/min	2.8 MAX
Tappi T555		
EDGEWICK - LA/23 TP84010	Kg/m <sup>2</sup> /Hour	1.4 MAX
STRETCH MD CD	%	2.0 MIN 5.0 MIN
Tappi T 494		

**Construction**



**Note :**

- 1.) All Properties are according to ITC Limited, PSPD Unit:BOL Measurements
- 2.) Test Climate 23°C ± 1 & 50% ± 2 RH
- 3.) Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples
- 4.) This product can be serviced with FSC Mix. Certificate Registration Code: SW CoC 004747 - B

ACCEPTED BY	HEAD MARKETING (PSPD)	ISSUED BY	UNIT HEAD (BOL)
SIGNATURE		SIGNATURE	